



**Metallurgical
Laboratories**

Date: November 27, 2018

ANALYSIS REPORT:

To: Pershing Resources Company
200 South Virginia Street 8th Floor,
Reno, Nevada 89501

AuRIC Sample No.:	4771	4772	4773
Customer Sample ID No.:	Bag 1	Bag 2	Bag 3
Method (Code 1 / Code 2)	(AD3/ICPE)	(AD3/ICPE)	(AD3/ICPE)
Units:	(ppm)	(ppm)	(ppm)
Ag	32.8	30.3	52.0
Al (wt %)	0.496%	0.460%	0.333%
As	493.3	103.3	205.5
Au	1.3	3.2	2.0
B	34.1	40.7	44.9
Ba	436.6	187.5	260.9
Be	1.7	0.9	0.4
Bi	3.1	4.0	8.4
Ca (wt %)	0.966%	<0.100%	<0.100%
Cd	20.0	7.2	9.0
Co	7.2	8.7	8.6
Cr	9.5	26.6	29.1
Cu	1,454.9	412.7	740.1
Fe (wt %)	2.811%	3.969%	3.601%
Ga	N/D	N/D	N/D
Hg	N/D	N/D	N/D
Ir	N/D	N/D	N/D
K (wt %)	0.331%	0.641%	0.490%
La	6.4	45.1	38.7
Mg (wt %)	<0.100%	<0.100%	<0.100%
Mn	574.1	57.4	52.9
Mo	5.5	18.8	17.8
Na (wt %)	<0.100%	<0.100%	<0.100%
Ni	1.1	1.0	2.3
Os	N/D	N/D	N/D
P	460.0	150.0	58.6
Pb	4,100.4	2,901.0	10,346.2
Pd	N/D	N/D	N/D
Pt	N/D	N/D	N/D
Rh	N/D	N/D	N/D
Ru	N/D	N/D	N/D
S	10,947.4	16,725.4	18,420.8
Sb	20.9	11.7	8.6
Sc	0.7	0.3	0.1
Si (wt %)	N/A	N/A	N/A
Sr	38.8	31.2	27.7
Th	13.8	21.1	22.6
Ti	20.9	11.7	18.5
Tl	N/D	N/D	N/D
U	N/D	N/D	N/D
V	N/D	N/D	N/D
Zn	2,953.9	2,435.6	704.4

Analysis method:

Code 1

ADn
FAL
FAN
FAT

Procedure for Decomposition / Preparation of Solid Samples

Acid Decomposition (n: the number of acids used)
Fire Assay with Lead button Collection
Fire Assay with Nickel Sulfide Collection
Fire Assay with Tin Button Collection

Code 2

VOL
GRV
FAA
GAA
ICPE

Procedure for Measurement

Volumetry or Titrimetry
Gravimetry
Flame Atomic Absorption Spectrophotometry
Graphite Furnace Atomic Absorption Spectrophotometry
Inductively Coupled Plasma Spectrophotometry

Miscellaneous

N/A Not assayed
N/D Not detected

GENERAL DISCLAIMER:

The results reported above are based on well-known, accepted analytical procedures used solely on the sample submitted by the customer. No warranty as to the reproducibility or extractability of the material other than the sample is given. AuRIC Metallurgical Laboratories, LLC makes no representation express or implied on the material other than that represented by the assayed sample.

Ahmet B. Altinay
Metallurgical Engineer



**Metallurgical
Laboratories**

Date: November 27, 2018

ANALYSIS REPORT:

To: Pershing Resources Company
c/o Mr. Joel Adams,
200 South Virginia Street 8th Floor,
Reno, Nevada 89501

Sample No:	Customer Sample ID No:	Method Code1 Code2	Gold (Tr oz/ston)	Silver (Tr oz/ston)	Platinum (Tr oz/ston)	Palladium (Tr oz/ston)
13405	Bag 1	FAL/ICPE	0.038	0.900	----	----
13406	Bag 2	FAL/ICPE	0.094	0.903	----	----
13407	Bag 3	FAL/ICPE	0.059	1.673	----	----

Analysis method:

Code 1 **Procedure for Decomposition / Preparation of Solid Samples**
ADn Acid Decomposition (n: the number of acids used)
FAL Fire Assay with Lead button Collection
FAN Fire Assay with Nickel Sulfide Collection
FAT Fire Assay with Tin Button Collection

Code 2 **Procedure for Measurement**
VOL Volumetry or Titrimetry
GRV Gravimetry
FAA Flame Atomic Absorption Spectrophotometry
GAA Graphite Furnace Atomic Absorption Spectrophotometry
ICPE Inductively Coupled Plasma Spectrophotometry

Miscellaneous
N/A Not assayed
N/D Not detected

GENERAL DISCLAIMER:

The results reported above are based on well-known, accepted analytical procedures used solely on the sample submitted by the customer. No warranty as to the reproducibility or extractability of the material other than the sample is given. AuRIC Metallurgical Laboratories, LLC makes no representation express or implied on the material other than that represented by the assayed sample.

Ahmet B. Altinay
Metallurgical Engineer