

AMAK Mining Particulars

Description	Project-to-Date 6/30/2014	JORC Report
Years	2.0	11.5
Mined, DMT	1,439,000	8,266,000
Mill throughput, DMT	1,348,998	
Raw ore grade (average)		
Copper	1.36%	
Zinc	3.17%	
Concentrate grade (average)		
Copper	24.86%	
Zinc	50.55%	
Recovery (average)		
Copper	84.84%	
Zinc	74.21%	
Deductibles for metals payable		
Copper	1.00%	
Zinc	8.00%	
Precious metals		
Gold (grams/ton in zinc)	1.2	
Gold (grams/ton in copper)	2.9	
Silver (grams/ton in zinc)	78.8	
Silver (grams/ton in copper)	107.8	